

ARTICLE

Received 8 Dec 2014 | Accepted 18 Feb 2015 | Published 26 Mar 2015

DOI: 10.1038/ncomms7668

OPEN

Ternary metal fluorides as high-energy cathodes with low cycling hysteresis

Feng Wang¹, Sung-Wook Kim^{1,†}, Dong-Hwa Seo^{2,3,†}, Kisuk Kang^{2,3}, Liping Wang¹, Dong Su⁴, John J. Vajo⁵, John Wang⁵ & Jason Graetz^{1,5}

Transition metal fluorides are an appealing alternative to conventional intercalation compounds for use as cathodes in next-generation lithium batteries due to their extremely high capacity (3–4 times greater than the current state-of-the-art). However, issues related to reversibility, energy efficiency and kinetics prevent their practical application. Here we report on the synthesis, structural and electrochemical properties of ternary metal fluorides ($M^1_y M^2_{1-y} F_x$; $M^1, M^2 = \text{Fe, Cu}$), which may overcome these issues. By substituting Cu into the Fe lattice, forming the solid-solution $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$, reversible Cu and Fe redox reactions are achieved with surprisingly small hysteresis (<150 mV). This finding indicates that cation substitution may provide a new avenue for tailoring key electrochemical properties of conversion electrodes. Although the reversible capacity of Cu conversion fades rapidly, likely due to Cu^+ dissolution, the low hysteresis and high energy suggest that a Cu-based fluoride cathode remains an intriguing candidate for rechargeable lithium batteries.

¹Sustainable Energy Technologies Department, Brookhaven National Laboratory, Upton, New York 11973, USA. ²Department of Materials Science and Engineering, Research Institute of Advanced Materials, Seoul National University, Seoul 151-742, Republic of Korea. ³Center for Nanoparticle Research, Institute for Basic Science, Seoul National University, Seoul 151-742, Republic of Korea. ⁴Center for Functional Nanomaterials, Brookhaven National Laboratory, Upton, New York 11973, USA. ⁵Sensors and Materials Laboratory, HRL Laboratories, LLC, Malibu, California 90265, USA. † Present address: Nuclear Fuel Cycle Process Development Group, Korea Atomic Energy Research Institute, Daejeon 305-353, Republic of Korea (S.-W. Kim); Department of Materials Science and Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, USA (D.-H. Seo). Correspondence and requests for materials should be addressed to F.W. (email: fwang@bnl.gov).

Lithium ion batteries (LIBs) are the preferred energy storage devices for portable electronics, and their use in electric vehicles and grid-level energy storage is increasing rapidly^{1–3}. However, large-scale application requires greater energy density per unit cost (by two times or more) for widespread use. The capacity of conventional cathodes (for example, LiCoO₂, LiFePO₄) is low (140–170 mAh g⁻¹) and currently limits the energy density of most commercial cells. Although a number of alternative anodes (such as Si and Sn) exhibit capacities well above 500 mAh g⁻¹, few cathodes have been identified that can match such high capacity. The conversion cathodes, specifically the fluoride-based materials, are an exception to this rule and exhibit extremely high specific capacities, enabled by more than one electron transfer per transition metal ($M^{n+}X_y + nLi^+ + ne^- = yLi_{n/y}X + M^0$; $n \geq 2$)^{4–7}, in addition to their intrinsically high redox potentials (>2 V)^{5,8–18}. CuF₂ is particularly attractive because of its extremely high theoretical potential (~3.55 V) and specific capacity (~528 mAh g⁻¹), offering an exceptionally high specific energy density (1,874 Wh kg⁻¹)^{8,9}. However, the electrochemical activity of CuF₂ is low, and utilization of its full capacity was only recently achieved by embedding CuF₂ into a conductive matrix¹³. Unfortunately, the utility of CuF₂ has been limited to primary batteries due to the irreversibility of the Cu^{2+/0} redox reaction. Other fluorides, such as FeF₂ and FeF₃ exhibit high reversibility^{15–18}, but their low working potentials and poor energy efficiency (due to large polarization and cycling hysteresis), continue to limit their practical use in commercial batteries.

Recently, extensive research on metal fluoride cathodes has provided new insights into the mechanisms involved in the conversion reactions and the issues relevant to cycling reversibility and efficiency (for example, hysteresis)^{8–21}. Although poor electronic and ionic transport plague many conversion electrodes, recent studies show that the electronic conductivity in FeF₂ improves lithiation and approaches that of metallic Fe (ref. 20). The percolating Fe network formed during lithiation provides a facile electronic pathway^{15,16,19,20}, and the high interfacial area provides abundant pathways for rapid Li⁺ transport^{15,22}. In contrast, the conversion reaction in CuF₂ involves highly mobile Cu²⁺ ions, which leads to coarsening and growth of large, isolated Cu particles during lithiation, making reconversion difficult^{15,17}. In addition, a recent study of the CuF₂ conversion reaction by Hua *et al.*²³, clearly showed that the dominant reaction occurring during the 1st charge is the dissolution of Cu into the electrolyte to form an unidentified Cu⁺ species, resulting in considerable loss of capacity. An intriguing new concept, derived from these recent findings, is the possibility of substituting Cu into the Fe fluoride system, and thereby forming a ternary solid–solution Cu_yFe_{1-y}F₂. An electrode configured in this way would potentially benefit from the percolating iron network, which may be effective at ‘trapping’ Cu ions allowing them to fully oxidize into Cu²⁺. The addition of a second cation into a solid–solution is also an effective strategy for tailoring electrochemical properties (thermodynamics and kinetics) and improving electrochemical performance, as already demonstrated in many electrodes^{24–28}. Surprisingly, despite tremendous research on the binary metal fluorides^{8–20}, studies of conversion reactions in the ternary fluorides (involving two transition metal cations) have been largely overlooked.

In this study, solid solutions of the ternary metal fluorides M¹_yM²_{1-y}F_x (M¹, M² = transition metal), were prepared via mechanochemical reactions. The structure, stability and electrochemical properties of Cu_yFe_{1-y}F₂ were investigated by density functional theory (DFT) calculations, electrochemical measurements, along with comprehensive structural and chemical

analysis using synchrotron X-ray diffraction (XRD), absorption spectroscopy (XAS) and (scanning) transmission electron microscopy ((S)TEM) coupled with electron energy loss spectroscopy (EELS). Electrochemical measurements indicated a reversible Cu redox reaction (that is, Cu^{2+/0}) in the mixed system, Cu_{0.5}Fe_{0.5}F₂, in contrast to irreversible behaviour observed in the binary fluoride, CuF₂ (ref. 23). This result was subsequently confirmed by XAS and TEM–EELS measurements. The voltage hysteresis for the Cu redox (Cu^{2+/0}) in Cu_yFe_{1-y}F₂ is surprisingly small, <148 mV, which is likely to be the lowest value ever measured for conversion reactions in metal fluorides. A comprehensive investigation of the reaction mechanisms, thermodynamics and kinetics of the lithium (re)conversion reactions in the solid–solution Cu_yFe_{1-y}F₂ reveals that the incorporation of Cu into the Fe lattice enables a cooperative redox reaction, which leads to the reversible Cu redox (Cu^{2+ ↔ Cu⁰}).

Results

Structure of ternary metal fluorides. The crystal structures of as-synthesized M¹_yM²_{1-y}F₂ powders were examined using synchrotron XRD and TEM. Figure 1a shows the XRD patterns of the Cu_yFe_{1-y}F₂ system at several different Cu/Fe ratios ($y = 0, 0.1, 0.33, 0.5, 0.67, 0.9, 1$). The broadened diffraction peaks indicate a loss of long-range order during the mechanochemical synthesis. Interestingly, the milling of CuF₂ and FeF₂ precursors leads to the formation of a single solid–solution phase over the entire compositional range. This is not too surprising given the similarity of the CuF₂ and FeF₂ structures. FeF₂ exhibits a tetragonal rutile structure (space group: P4₂/mnm) and is comprised of FeF₆ octahedra, while CuF₂ is monoclinic (space group: P2₁/n), which is essentially a distorted rutile structure due to the strong Jahn–Teller distortion induced by the Cu²⁺ ([Ar]3d⁹) ion (Fig. 1b and Supplementary Fig. 1)²⁷. The distorted structure of CuF₂ becomes more symmetric with Fe incorporation as the Cu_yFe_{1-y}F₂ solid–solution is formed (see Supplementary Fig. 2 and Supplementary Note 1). The as-synthesized samples are complex agglomerates of small nanocrystallites as shown by brightfield TEM image (<10 nm; Fig. 1c). The diffuse rings in the electron diffraction pattern (although being broadened due to the nanocrystalline nature of the particles; inset in Fig. 1c) can be assigned to the tetragonal rutile phase (Supplementary Fig. 3), consistent with the XRD measurements (Fig. 1a).

DFT calculations were used to predict the stability of solid–solution phases, at all the possible configurations (see details in Methods below). The energy difference between the possible Cu_yFe_{1-y}F₂ phases and the simple yCuF₂–(1-y)FeF₂ mixture (Fig. 1d) indicates that, regardless of the composition, there exist several Cu_yFe_{1-y}F₂ phases that are energetically more stable (negative energy points) than the simple mixture (zero energy points). The lowest energy points at each composition overlap well with the convex hull (dashed line), indicating that Cu_yFe_{1-y}F₂ can exhibit solid–solution behaviour over the entire composition range. The structural stability of the solid–solution phase was experimentally confirmed by *in situ* XRD (Fig. 1e), which shows no phase decomposition in Cu_{0.5}Fe_{0.5}F₂ during dynamic heating up to 250 °C.

Since most of the 3d metal binary fluorides (that is, MF₂) have similar structures, either based on the tetragonal rutile or distorted rutile framework, it is expected that they may form a variety of solid solutions. A number of ternary fluoride phases were prepared, including Cu_{0.5}Ni_{0.5}F₂, Fe_{0.5}Ni_{0.5}F₂, Ni_{0.5}Co_{0.5}F₂ and Fe_{0.5}Co_{0.5}F₂ (Fig. 1f), which demonstrates the versatility of the mechanochemical synthesis method.

Electrochemical properties of Cu_yFe_{1-y}F₂. Electrochemical measurements were performed on a series of Cu_yFe_{1-y}F₂ samples

to evaluate their electrochemical properties in the presence of two redox centers (Fig. 2). During galvanostatic discharge, $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ exhibits a two-step lithiation process as expected (Fig. 2a), but the voltage profiles are different than those obtained from pure CuF_2 , FeF_2 or a mixture of the two. In $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$, the Cu conversion (higher plateau) occurs at similar potentials as CuF_2 , while the Fe conversion (lower plateau) occurs at a much higher potential and does not exhibit the voltage dip typically observed in pure FeF_2 , indicating a more facile Fe conversion.¹⁵ Even at low Cu concentration (for example, 10%), significantly higher rate capabilities were achieved in $\text{Cu}_{0.1}\text{Fe}_{0.9}\text{F}_2$ at room temperature (Supplementary Fig. 4). Similar to other solid-solution systems^{26–28}, the electrochemical properties in the ternary system, $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$, are significantly affected by the cooperative redox of Cu and Fe sitting on the same lattice.

Electrochemical analysis of $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ over the voltage range of 1.0–4.5 V (Fig. 2b) revealed an initial discharge capacity is $\sim 575 \text{ mAh g}^{-1}$, comparable to the theoretical value (549 mAh g^{-1} for two electron transfer), and a charge capacity 543 mAh g^{-1} ($\sim 94\%$ of the initial discharge capacity), indicating the reoxidation of both the iron and the copper. The reaction process during the subsequent charge and discharge appear to be different than that during the first discharge, as evidenced by the change from two obvious plateaus (~ 2.9 and ~ 2.2 V) to three plateaus (~ 2.8 , 3.4 , 3.8 V). On subsequent cycles the voltage profiles become similar, indicating a high cycling reversibility. The redox reactions in the $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ electrodes were also

investigated by cyclic voltammetry (CV), as given in Fig. 2c, and compared with FeF_3 (ref. 14). During charge, the first peak is attributed to $\text{Fe}^{0/2+}$ oxidation (at ~ 2.8 V), while the second, located at ~ 3.4 V, is likely attributed to the further oxidation into trivalent iron (Fe^{3+}). The third peak at higher voltage (~ 3.8 V) is noticeably absent in the CV from FeF_3 and must be related to Cu oxidation since there are no other redox centers in this voltage range. There are also three peaks in the 2nd discharge, with the first two associated with $\text{Fe}^{2+/0}$ and $\text{Fe}^{3+/2+}$ reduction and a 3rd at ~ 3.4 V assigned to $\text{Cu}^{2+/0}$ reduction (with the voltage slightly lower than the theoretical value of 3.5 V). The voltage of $\text{Cu}^{2+/0}$ reduction during the 1st discharge is relatively low (only about 2.9 V), which is due to a kinetic effect common in conversion reaction electrodes¹⁵. In contrast to pure CuF_2 , which showed no reversible redox Cu peaks, the redox peaks in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ are present over multiple cycles, indicating different electrochemical behaviour in the solid-solution ternary phase (See Supplementary Fig. 5 and Supplementary Note 2 for comparison of Cu redox reactions between CuF_2 and $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$).

Another striking feature observed in the cycling data is the small voltage hysteresis. Even during conventional galvanostatic cycling (Fig. 2b), the measured voltage gaps are only ~ 0.48 V for $\text{Cu}^{0/2+}$, ~ 0.63 V for $\text{Fe}^{0/2+}$ and ~ 0.43 V for $\text{Fe}^{2+/3+}$. Those values are significantly less than that of binary fluorides, such as FeF_2 , which is ~ 1.6 V (see Supplementary Fig. 6). The voltage hysteresis measured by galvanostatic intermittent




Figure 1 | Structure and stability of novel ternary metal fluorides. (a) Synchrotron XRD patterns from $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ along with CuF_2 (JCPDS#42-1244) and FeF_2 (JCPDS#45-1062), (b) schematic illustration of the FeF_2 (rutile) and CuF_2 (distorted rutile) structures, (c) high-resolution TEM image of as-synthesized $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ nanocrystallites (inset: electron diffraction pattern from a large area), (d) energy diagram of $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ phases (at various possible configurations) predicted by DFT calculations, (e) *in situ* XRD patterns recorded during heating of $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ from room temperature (R.T.) to 250 °C, (f) XRD patterns from representative ternary fluorides of varying metal species, $\text{M}^1_{0.5}\text{M}^2_{0.5}\text{F}_2$ ($\text{M}^1, \text{M}^2 = \text{Cu, Fe, Ni, Co}$).

titration technique (GITT) is reduced to 148 mV for the $\text{Cu}^{0/2+}$ redox and ~ 200 mV for the Fe redox (Fig. 2d), which is substantially lower than pure FeF_2 (700 mV)²⁰ and comparable to intercalation-type electrodes. This is the lowest reported hysteresis for conversion reaction in any metal fluoride, indicating the potential for achieving high-energy efficiency in ternary fluoride cathodes. In addition, these results also suggest that the hysteresis is not solely determined by the anions, but is also affected by the type of cations present. This is further verified by the different thermodynamic and kinetic behaviours between $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ and pure FeF_2 , CuF_2 (Supplementary Figs 4 and 7 and Supplementary Note 3).

Reversibility of redox reactions in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$. Elemental specific XAS measurements were performed on $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ to gain insight into the Cu and Fe redox reactions and local structural reorganization, and to correlate these results with the electrochemical behaviour. Figure 3 shows the results from XAS near-edge structure (XANES) and extended fine structure (EXAFS) measurements of Fe and Cu K-edges during the 1st cycle. On discharge, the XANES spectra clearly indicate the conversion of Cu occurs first (#1 \rightarrow #4), followed by that of Fe (#4 \rightarrow #8) at lower voltages (Fig. 3b,e). The XANES spectra from the Cu K- (Fig. 3b) and Fe K-edges (Fig. 3e) reveal an isosbestic point (as labelled by an arrow), indicating a two-phase transition behaviour of the conversion reactions. Simultaneous dissociation of Cu–F/Fe–F bonds and the formation of metallic Cu–Cu/Fe–Fe bonds at each plateau were also confirmed by the Fourier transformation (FT) of the EXAFS (Fig. 3c,d,f,g). XRD measurements (Supplementary Fig. 8) also show decomposition of the initial solid-solution phase and formation of metallic Cu^0 after the high-voltage plateau, while there is no visible diffraction peak from FeF_2 , indicative of the highly disordered nature of the FeF_2 after Cu conversion. The intermediate FeF_2 is then reduced to metallic Fe^0 at lower voltages, (Fig. 3e,f).

The charge process is quite different from the discharge as shown in Fig. 3h–j. At the initial stage of charge (#8 \rightarrow #9), the Fe oxidation state increases from 0 to 2+ (Fig. 3h). On further delithiation (#9 \rightarrow #11), the oxidation state of Fe continues to increase (indicated by edge shift to higher energies), along with the formation of a 2nd isosbestic point indicating the further oxidation of Fe^{2+} to a higher valence state, but only partially (as verified by XANES of Fe K-edge; Supplementary Fig. 9)²⁹. This is in agreement with the CV data, which shows a redox peak at ~ 3.4 V (Fig. 2c). The strong Fe–F peak, with bond distance similar to that of FeF_6 octahedra in a rutile phase, is evident in the final product (Fig. 3i), suggesting the reconversion back to a rutile-like framework.

In the high-voltage region (above 3.5 V; #10 \rightarrow #11), the shift of the Cu K-edge to higher energies provides direct experimental evidence for oxidation of Cu^0 back to a high-valence state (Fig. 3h). In addition, the reformation of the Cu–F bonds is evident from the FT EXAFS data (Fig. 3j), showing a strong Cu–F peak with exactly the same position and shape as in the pristine material. Due to the over oxidation of Fe to Fe^{3+} during which extra LiF is consumed, Cu^0 cannot be fully oxidized into Cu^{2+} . But it should be noted that, Fe is only partially oxidized into Fe^{3+} (as verified by XANES of Fe K-edge in Supplementary Fig. 9), allowing much of the Cu to be converted to Cu^{2+} , while the rest remains as Cu^0 (Figs 3j and 4c). These results provide direct verification of a reversible Cu redox ($\text{Cu}^{0/2+}$) in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ (as observed in Fig. 2). This behaviour is different than what is observed in pure CuF_2 , as indicated by the valence state and local coordination of Cu after one complete discharge/charge cycle (Supplementary Fig. 10 and Supplementary Note 4). Although Cu^{2+} is fully reduced to metallic Cu^0 during the 1st discharge, Cu is only partially oxidized (to a soluble Cu^+) in pure CuF_2 during the first charge (delithiation)²³. The extent of Cu oxidation on charge is significantly higher in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ (even after four cycles) as evidenced in the Cu K-edge XANES. While




Figure 2 | Electrochemical properties of $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ solid-solution. (a) Voltage profiles (first discharge at a current 5 mA g^{-1}) of the $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ series along with a simple mixture of CuF_2 and FeF_2 (b) voltage profiles of $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ for the first five cycles (9.2 mA g^{-1}), (c) cyclic voltammetry (CV) curves for the first (red) and second (black) cycles at a rate of $C/40$, in comparison to that of FeF_3 (adapted from ref. 14), (d) quasi-equilibrium voltage profile from $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ obtained from galvanostatic intermittent titration technique (GITT) measurements (inset; 150 mA g^{-1} for 3.5 h followed by a 15 h rest). All the measurements were performed at room temperature.

the local coordination of Cu in the reconverted CuF_2 forms a doublet and is distinctly different from that in the pristine CuF_2 , or reconverted $\text{Cu}_y\text{Fe}_{1-y}\text{F}_x$, in which only a single Cu–F peak was observed. The Cu valence state and coordination in the reconverted $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ is also different than other Cu^+ compounds, such as CuCl , but similar to that of “ $0.5\text{Cu}^0 + 0.5\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ ” (Supplementary Fig. 11).

Due to the disordered nature of phases formed during conversion and reversion in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_x$, their structures were not identified from XRD measurements (Supplementary Fig. 8), but well resolved locally by electron diffraction and STEM–EELS (Supplementary Fig. 12 and Supplementary Note 5). The most salient feature of these results is that most of the Cu and Fe are atomically mixed both in the pristine and reconverted states, although some larger (presumably inactive) Cu particles were observed in the EELS maps (Supplementary Fig. 12a–e). The near-edge features of the Cu L-edge, such as the Cu L_3 peak at ~ 933 eV, clearly shows that Cu in the reconverted phase is nearly identical to that in the pristine material (Supplementary Fig. 12f); nevertheless the Cu K-edge spectra in the discharged samples (at 2.4 and 1.5 V) show broad plateaus characteristic of metallic Cu (additional details in Supplementary Note 5). These results are consistent with observations in the Cu K-edge XANES and EXAFS measurements, indicating the reversion of Cu back to a state close to Cu^{2+} (bonded with F). Although no peaks associated with the rutile-like structure were identified by XRD (Supplementary Fig. 8), the

electron diffraction pattern, recorded from localized regions of the reconverted $\text{Cu}_y\text{Fe}_{1-y}\text{F}_x$ (Supplementary Fig. 12g), shows diffusive rings that are overall similar to those from the pristine sample, indicating the reformation of rutile-like structure in the $\text{Cu}_y\text{Fe}_{1-y}\text{F}_x$ electrodes after charge, consistent with the Cu K-edge EXAFS results (Fig. 3j).

Evolution of Cu in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ during cycling. To track the valence state and local coordination of Cu and better understand Cu redox behaviour in a working electrode, *in situ* XAS measurements (XANES and EXAFS of Cu K-edge) were performed on the $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ electrodes, with hundreds of spectra acquired during the 1st one and half cycles. Since the Cu reduction during the first discharge is well understood, only the results from the first charge and second discharge are presented here (Fig. 4). The results from *in situ* XAS measurements during charge (Fig. 4b,c) reveal a gradual Cu oxidation from Cu^0 to Cu^{2+} as indicated by the gradual chemical shift to higher energies, and the formation of the Cu–F bonds as indicated by growth of Cu–F peak in the FT of EXAFS (up to an amplitude similar to that of the pristine sample). This process is reversed on discharge (second lithiation) where the Cu K-edge shifts to lower energies and the Cu–F peak in the FT EXAFS data disappears as Cu is reduced back to the metallic state (Fig. 4d,e). This behaviour is distinctly different than what was observed in the CuF_2 electrode, in which no




Figure 3 | Reversible redox reactions of Cu and Fe in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$. (a) Typical voltage profile of $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ for the first cycle with labels of various (de)lithiated states (#1–#11) for samples used in XAS measurements, (b–j) near-edge XAS spectra (XANES) and Fourier transformation (FT) of extended fine structure (EXAFS) for both Fe and Cu edges, with (b,c,d) for the first lithiation stage (#1–#4), (e,f,g) for the second lithiation stage (#4–#8) and (h–j) for the delithiation process (#8–#11) compared with the pristine material (#1). Isosbestic points in the XANES spectra (indicating two-phase behaviours) are labelled by arrows.

further reduction was found during the second cycle (Supplementary Fig. 10, and Supplementary Note 4, and also reported in ref. 23). These results provide direct evidence verifying a reversible Cu redox process in the $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ electrode (which does not occur in CuF_2). In addition, the isosbestic points in the XANES data during the first charge and second discharge suggest the dominant reaction is two phase, involving $\text{Cu}^0 \leftrightarrow \text{Cu}^{2+}$, without going through a Cu^+ intermediate (such as Cu-F ; being consistent with DFT calculations in Supplementary Fig. 13 and Supplementary Note 6). Despite these results, analysis of the internal cell components after cycling indicates that some Cu dissolution (Cu^+) still occurs in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ and these parasitic reactions are likely responsible for much of the capacity fade in this system (see Supplementary Fig. 14 and Supplementary Note 7). Various mitigation methods, such as surface coatings to stabilize the electrode at high potentials or barrier layers to prevent crossover, may be useful at limiting the loss of Cu and mitigating the capacity decay^{30,31}.

Although Cu reoxidation is expected to occur at voltages above 3.55 V during charge (considering the overpotential), the *ex situ* XAS results clearly reveal a slight chemical shift in the Cu K-edge along with the formation of a surprisingly large Cu-F peak in the FT EXAFS in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ charged to only 3.5 V (with a 10-h hold; Fig. 3h,j). The Cu reoxidation at low potentials is evident in the *in situ* XAS data (Fig. 4), particularly by the formation of a small Cu-F peak in the FT EXAFS (spectrum #82 in Fig. 4c) at potentials as low as ~ 1.5 V. This peak occurs almost simultaneously with the Fe reconversion ($\text{Fe}^{0/2+}$), and gradually grows into an intense

peak at 3.5 V (spectrum #126). These results indicate that Cu reconversion is initiated at low potentials and largely overlaps with Fe oxidation, which may consequently lead to the reformation of the solid-solution phase ($\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$). This newly reformed $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ phase has a somewhat disordered structure, but remains a rutile-like framework, similar to the pristine material. This repeatable, cooperative redox behaviour (after the first discharge) may also explain the origin of the reversibility in this system (Fig. 2b,c). The disclosed cooperative redox behaviour in ternary fluorides may also be widely applicable to other systems, such as multication oxides or oxyfluorides^{32,33}, provided that solid-solution phases can be formed.

Discussion

A summary of the reaction pathway and phase evolution in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ is illustrated in Fig. 5. During the initial discharge, the conversion process occurs in two stages (*I* and *II*), which involve the reduction of Cu and Fe, while the reversion (*III* and *IV*) is more complicated, and follows a different pathway. The reactions in Stage *III* start with Fe reversion to FeF_2 , followed by transformation into a rutile-like iron fluoride (with Fe at a valence of $\text{Fe}^{2+/3+}$). The reversion of Cu is initiated at the very beginning of Stage *III*, triggered by the preformed rutile-like framework. Due to the structural similarities, the nucleation and subsequent growth of the Cu-based fluoride phase on the surface of rutile-like iron fluoride likely requires less energy than direct nucleation of CuF_2 , which could reduce the overpotential and enable the reversion at very low potentials, leading to




Figure 4 | *In situ* XAS of reversible Cu oxidation/reduction in $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$. (a) Voltage profile for the 1st cycle and 2nd discharge, (b,c) XANES and FT EXAFS for Cu K-edge during 1st charge (Cu oxidation), (d,e) XANES and FT of EXAFS for the Cu K-edge during the 2nd discharge (Cu reduction). Isosbestic points in the XANES spectra are labelled by arrows.




Figure 5 | Schematic illustration of the asymmetric reaction pathway in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$. Cu and Fe reduction occurs sequentially during discharge (Stages I and II), while the Fe and Cu oxidation processes (III and IV) overlap during charge, which enables the reformation of a disordered rutile-like Cu-Fe-F phase.

formation of the Cu-Fe-F-based rutile structure. As the potential is further increased (in Stage IV), much of the Cu is reconverted back to the rutile structure, with a small amount of irreversible Cu dissolved into the electrolyte or segregated into larger, isolated particles (see Supplementary Figs 12 and 14 and Supplementary Note 7). So consequently, the converted phase may not be $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$, but a Cu-deficient phase, such as $\text{Cu}_{0.35}\text{Fe}_{0.65}\text{F}_2$ or other compositions, as being predicated by DFT calculations (Fig. 1d).

The revealed reaction pathway and correlated local structural reorganization may help to understand the small overpotential and strikingly low voltage hysteresis in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_x$ (Fig. 2). First the formation of nanosized FeF_2 intermediates, surrounded by metallic Cu^0 from Cu conversion (Supplementary Fig. 12a–e), may accelerate the Fe conversion due to the increased ionic conductivity (resulting from the large LiF/FeF_2 interface) and the enhanced electronic transport (in the presence of metallic Cu^0)^{15,16}. The increase in defects and structural disorder, along with the size reduction of the FeF_2 after Cu conversion is likely responsible for the higher discharge potential during the initial Fe conversion. Similar observations of elevated conversion potential were also reported in amorphous RuO_2 (compared with crystalline phase)³⁴. The low voltage hysteresis associated with the Cu redox (Fig. 2d) is most likely due to the low nucleation barrier for Cu-F formation on/within the existing Fe-F framework. In addition, the structural disorder of the reformed Cu-Fe-F framework, and the intrinsically high mobility of Cu ions may also play a role.

In conclusion, novel ternary metal fluorides $\text{M}^1_y\text{M}^2_{1-y}\text{F}_x$ ($\text{M}^1, \text{M}^2 =$ transition metal) were prepared by a mechanochemical process to form a variety of solid solutions, which exhibit interesting electrochemical properties. The initial conversion reaction (lithiation) in $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ proceeds via a two-stage process, the reduction of Cu to metallic Cu^0 and concomitant formation of disordered FeF_2 , followed by $\text{Fe}^{2+/0}$ reduction. The reformation of the fluoride takes a different path, during which

Fe^0 is partially oxidized up to Fe^{3+} , leading to the formation of a rutile framework, which promotes the reversion of Cu to form a disordered rutile-like Cu-Fe-F final phase (overall similar to the pristine material). However, the formation of some trivalent iron limits the full reversion of Cu^0 back to Cu^{2+} . Although cation dissolution remains a challenge for the long-term cyclability, the Cu-based ternary fluorides exhibit two truly unique electrochemical properties—a reversible $\text{Cu}^{2+/0}$ reaction and remarkably low hysteresis (<150 mV), which, along with intrinsically high voltage and capacity, makes them appealing for use in next-generation rechargeable batteries.

Methods

Synthesis of $\text{M}^1_y\text{M}^2_{1-y}\text{F}_2$ solid-solution. As-purchased CuF_2 (Aldrich, 98%), FeF_2 (Aldrich, 98%), NiF_2 (Aldrich, 98%) and CoF_2 (Aldrich, 98%) were used as starting materials without any further purification. A stoichiometric mixture of two MF_2 compounds was introduced into a stainless steel reactor inside an Ar-filled glove box. The reactor was sealed to prevent air contamination and transferred to planetary ball-mill (Fritsch, Pulverisette 6). The mixed powder was ball-milled at 300 r.p.m. for 12 h. After the milling, the container was opened inside the Ar glove box to collect the final product for characterization.

DFT calculations. All DFT calculations were performed with the spin-polarized generalized gradient approximation (GGA) within the Perdew–Burke–Ernzerhof (PBE) functional³⁵. A plane-wave basis set and the projector-augmented wave method were used, which were implemented in the Vienna *ab initio* simulation package (VASP)³⁶. The Hubbard parameters (GGA + U) were used to correct the incomplete cancellation of the self-interaction of the GGA³⁷. An effective U -value of 5.3 eV for Fe ion and 4.0 eV for Cu ion were used^{38,39}. A plane-wave basis set with a kinetic energy cutoff of 500 eV and $6 \times 4 \times 4$ Monkhorst-Pack k-point meshes were used to ensure that the total energies converged to less than 5 meV per formula unit. To investigate the phase stabilities of $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$ ($0 \leq y \leq 1$), we calculated all possible Cu/Fe configurations within triple-sized supercells expanded along one of the axes. We considered 135 configurations within the distorted rutile structure and 78 configurations within the tetragonal rutile structure. All symmetrically distinct configurations were generated with a Cluster-Assisted Statistical Mechanics program⁴⁰. Two-hundred and thirteen configurations of different Cu contents were used in calculating the DFT formation energies (as shown in Fig. 1d). The dashed line shows the convex hull of $\text{Cu}_y\text{Fe}_{1-y}\text{F}_2$, when CuF_2 and FeF_2 are considered as the end members.

Characterization of as-synthesized materials. Crystal structures were determined by synchrotron XRD at beam line X14A at the National Synchrotron Light Source (NSLS; $\lambda = 0.7787 \text{ \AA}$). The lattice parameters of the synthesized samples were calculated by Rietveld refinement using the Fullprof software⁴¹. *In situ* high temperature XRD measurements (up to 250°C) were also carried out to examine the phase stability. The $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ powder was sealed in a quartz tube in the Ar-filled glove box and resistively heated during XRD measurements. High-resolution (S)TEM images, electron diffraction patterns and EELS mapping were collected from a JEOL TEM machine (JEM 2100F) and a dedicated STEM (Hitachi, HD2700) equipped with an EELS detector (Gatan, Enfina).

Electrochemical tests. The cycling performance of $\text{Cu}_x\text{Fe}_{1-x}\text{F}_2$ was measured using the conventional composite electrode composed of active materials (72 wt.%), carbon black (18 wt.%) and polyvinylidene fluoride binder (10 wt.%), which were homogeneously mixed together in *N*-methyl-2-pyrrolidone (solvent). The mixed slurry was cast onto an Al foil and dried overnight. All test electrodes were prepared inside the Ar-filled glove box to prevent water absorption. The test electrodes were assembled into CR-2025/2032 type coin cells with Li metal counter electrodes, glass fibre separator (Whatman, GF/D) or a polymer membrane separator (Celgard, 2320) and 1 M LiPF_6 electrolyte dissolved in 1:1 (by volume) mixture of ethylene carbonate and dimethylcarbonate (DMC). The test cell was cycled using a battery cycler (Arbin Instrument, BT-2400) in constant current mode to collect the electrochemical data. CV measurements were performed using a Solatron 1286 Electrochemical Interface. Galvanostatic intermittent titration technique was performed by applying an intermittent current for 3.5 h followed by a 15 h rest. The pristine cells were cycled between 1.0 and 4.5 V at a current of 150 mA (equivalent to a rate of C/20 at constant current).

Ex situ XRD/XAS/TEM/SEM studies. $\text{Cu}_{0.5}\text{Fe}_{0.5}\text{F}_2$ samples at different (dis-)charge states were prepared by controlling the cutoff voltage or the cutoff time during the electrochemical reaction. The test cells after cycling were disassembled using the coin cell disassembler. The cycled electrodes were thoroughly rinsed with DMC and then carefully collected inside the Ar-filled glove. For XRD and XAS measurement, the collected electrodes were sealed inside Kapton tape to minimize air exposure during the measurement.

In situ and *ex situ* XAS measurements (Cu K-edge and Fe K-edge) were performed at beam line X18A at the NSLS. The measurements were performed in transmission mode using a Si (111) double-crystal monochroator. Energy calibration for the absorption edge was made using Fe and Cu foils as a reference (Fe K-edge: 7112 eV; Cu K-edge: 8979 eV). A series of reference spectra (Fe K-edge and Cu K-edge) were recorded from Fe and Cu containing materials, including, FeF_2 , FeF_3 , FeO , Fe_2O_3 , CuF_2 , CuCl , CuCl_2 , CuO , Cu_2O . The XAS spectra were analysed using Athena⁴².

TEM samples were loaded onto a TEM holder inside the glove box and then transferred quickly to the TEM to minimize air exposure. The Li metal anode after one cycle was also collected, rinsed with DMC and then attached to carbon tape for SEM-EDS analysis inside the glove box. The SEM holder was sealed and then transferred quickly to the SEM to minimize air exposure.

References

- Tarascon, J.-M. & Armand, M. Issues and challenges facing rechargeable lithium batteries. *Nature* **414**, 359–367 (2001).
- Aricò, A. S., Bruce, P., Scrosati, B., Tarascon, J.-M. & Van Schalkwijk, W. Nanostructured materials for advanced energy conversion and storage devices. *Nat. Mater.* **4**, 366–377 (2005).
- Dunn, B., Kamath, H. & Tarascon, J.-M. Electrical energy storage for the grid: a battery of choice. *Science* **334**, 928–935 (2011).
- Poizot, P., Laruelle, S., Grugeon, S., Dupont, L. & Tarascon, J.-M. Nano-sized transition metal oxide as negative-electrode materials for lithium-ion batteries. *Nature* **407**, 496–499 (2000).
- Malini, P., Uma, U., Sheela, T., Ganesan, M. & Renganathan, N. G. Conversion reaction: a new pathway to realise energy in lithium-ion battery-review. *Ionics* **15**, 301–307 (2009).
- Cabana, J., Monconduit, L., Larcher, D. & Palacín, M. R. Beyond intercalation-based Li-ion batteries: the state of art and challenges of electrode materials reaction through conversion reactions. *Adv. Mater.* **22**, E170–E192 (2010).
- Yersak, T. A. *et al.* Solid state enabled reversible four electron storage. *Adv. Energy Mater.* **3**, 120–127 (2013).
- Amatucci, G. G. & Pereira, N. Fluoride based electrode materials for advanced energy storage devices. *J. Fluorine Chem.* **128**, 243–262 (2007).
- Li, H., Balaya, P. & Maier, J. Li-storage via heterogeneous reaction in selected binary metal fluorides and oxides. *J. Electrochem. Soc.* **151**, A1878–A1885 (2004).
- Badway, F., Cosandey, F., Pereira, N. & Amatucci, G. G. Carbon metal fluoride nanocomposites: structure and electrochemistry of FeF_3/C . *J. Electrochem. Soc.* **150**, A1209–A1218 (2003).
- Li, H., Richter, G. & Maier, J. Reversible formation and decomposition of LiF clusters using transition metal fluorides as precursors and their applications in rechargeable Li batteries. *Adv. Mater.* **15**, 736–739 (2003).
- Kim, S.-W., Seo, D.-H., Gwon, H., Kim, J. & Kang, K. Fabrication of FeF_3 nanoflowers on CNT branches and their application to high power lithium rechargeable batteries. *Adv. Mater.* **22**, 5260–5264 (2010).
- Badway, F. *et al.* Structure and electrochemistry of copper fluoride nanocomposites utilizing mixed conducting matrices. *Chem. Mater.* **19**, 4129–4141 (2007).
- Liu, P., Vajo, J. J., Wang, J. S., Li, W. & Liu, J. Thermodynamics and kinetics of the Li/FeF_3 reaction by electrochemical analysis. *J. Phys. Chem. C* **116**, 6467–6473 (2012).
- Wang, F. *et al.* Conversion reaction mechanism in lithium ion batteries: study of the binary metal fluoride electrodes. *J. Am. Chem. Soc.* **133**, 18828–18836 (2011).
- Wang, F. *et al.* Tracking lithium transport and electrochemical reactions in nanoparticles. *Nat. Commun.* **3**, 1201 (2012).
- Yamakawa, N., Jiang, M. & Grey, C. P. Investigation of the conversion reaction mechanisms for binary copper(II) compounds by solid-state NMR spectroscopy and X-ray diffraction. *Chem. Mater.* **21**, 3162–3176 (2009).
- Li, L., Meng, F. & Jin, S. High-capacity lithium-ion battery conversion cathodes based on iron fluoride nanowires and insights into the conversion mechanism. *Nano Lett.* **12**, 6030–6037 (2012).
- Parkinson, M. F., Ko, J. K., Halajko, A., Sanghvi, S. & Amatucci, G. G. Effect of vertically structured porosity on electrochemical performance of FeF_2 films for lithium batteries. *Electrochim. Acta* **125**, 71–82 (2014).
- Jonathan, K. K. *et al.* Transport, phase reactions, and hysteresis of iron fluoride and oxyfluoride conversion electrode materials for lithium batteries. *ACS Appl. Mater. Interf.* **6**, 10858–10869 (2014).
- Yu, H.-C. *et al.* Designing the next generation high capacity battery electrodes. *Energy Environ. Sci.* **7**, 1760–1768 (2014).
- Ma, Y. & Garofalini, S. H. Atomistic insights into the conversion reaction in iron fluoride: a dynamically adaptive force field approach. *J. Am. Chem. Soc.* **134**, 8205 (2012).
- Hua, X. *et al.* Comprehensive Study of the CuF_2 Conversion reaction mechanism in a lithium-ion battery. *J. Phys. Chem. C* **118**, 15169 (2014).
- Kang, K., Meng, Y. S., Bréger, J., Grey, C. P. & Ceder, G. Electrode with high power and high capacity for rechargeable lithium batteries. *Science* **311**, 977–980 (2006).
- Reed, J. & Charge, C. G. potential, and phase stability of layered $\text{Li}(\text{Ni}_{0.5}\text{Mn}_{0.5})\text{O}_2$. *Electrochem. Solid-State Lett.* **5**, A145–A148 (2002).
- Oh, M. H. *et al.* Galvanic replacement reaction in metal oxide nanocrystals. *Science* **340**, 964–968 (2013).
- Chatterji, T. & Hansen, T. C. Magnetoelastic effects in Jahn-Teller distorted CrF_2 and CuF_2 studied by neutron powder diffraction. *J. Phys: Condens. Matter.* **23**, 276007 (2011).
- Kim, H. *et al.* Multicomponent effects on the crystal structures and electrochemical properties of spinel-structured M_3O_4 ($\text{M} = \text{Fe}, \text{Mn}, \text{Co}$) anodes in lithium rechargeable batteries. *Chem. Mater.* **24**, 720–725 (2012).
- Kim, S.-W. *et al.* Energy storage in composite of a redox couple host and a lithium ion host. *Nano Today* **7**, 168–173 (2012).
- Jang, D. H., Shin, Y. J. & Oh, S. M. Dissolution of spinel oxide and capacity losses in 4V $\text{Li/LixMn}_2\text{O}_4$ cells. *J. Electrochem. Soc.* **143**, 2204–2211 (1996).
- Poizot, P. *et al.* Evidence of an electrochemically assisted ion exchange reaction in $\text{Cu}_{2.33}\text{V}_4\text{O}_{11}$ electrode material vs. Li. *Electrochem. Solid-State Lett.* **8**, A184–A187 (2005).
- Pereira, N., Badway, F., Wartelsky, M., Gunn, S. & Amatucci, G. G. Iron oxyfluorides as high capacity cathode materials for lithium batteries. *J. Electrochem. Soc.* **156**, A407–A416 (2009).
- Zhou, H. *et al.* Formation of iron oxyfluoride phase on the surface of nano- Fe_3O_4 conversion compound for electrochemical energy storage. *J. Phys. Chem. Lett.* **4**, 3798–3805 (2013).
- Delmer, O., Balaya, P., Kienle, L. & Maier, J. Enhanced potential of amorphous electrode materials: case study of RuO_2 . *Adv. Mater.* **20**, 501–505 (2008).
- Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized gradient approximation made simple. *Phys. Rev. Lett.* **77**, 3865–3868 (1996).
- Kresse, G. & Furthmüller, J. Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set. *Comp. Mater. Sci.* **6**, 15–50 (1996).
- Dudarev, S. L., Botton, G. A., Savrasov, S. V., Hymphreys, C. J. & Sutton, A. P. Electron-energy-loss spectra and the structural stability of nickel oxide: an LDA + U study. *Phys. Rev. B* **57**, 1505–1509.
- Ong, S. P. *et al.* Python materials genomics (pymatgen): a robust, open-source python library for materials analysis. *Comp. Mater. Sci.* **68**, 314–319 (2013).
- Jain, A. *et al.* Formation enthalpies by mixing GGA and GGA + U calculations. *Phys. Rev. B* **84**, 045115 (2011).

40. Van der Ven, A., Thomas, J. C., Xu, Q. & Bhattacharya, J. Linking the electronic structure of solids to their thermodynamic and kinetic properties. *Math. Comput. Simulat.* **80**, 1393–1410 (2010).
41. Rodriguez-Carvajal, J. Recent advances in magnetic structure determination by neutron powder diffraction. *Physica B* **192**, 55–69 (1993).
42. Ravel, B. & Newville, M. ATHENA, ARTEMIS, HEPHASTUS: Data analysis for X-ray absorption spectroscopy using IFEFFIT. *J. Synchrotron. Rad.* **12**, 537–541 (2005).

Acknowledgements

We thank Clare Grey and M. Stanley Whittingham for discussions concerning the conversion reaction mechanisms and for reviewing the manuscript. We thank colleagues Steven Ehrlich, Jianming Bai, Steve Greenbaum, Mallory Gobet, Young-Uk Park, LinSen Li, Lihua Zhang, Eric Stach, Vyacheslav Volkov, Lijun Wu and Yimei Zhu for discussion and technical support. The work was initiated by and supported as part of the NorthEastern Center for Chemical Energy Storage, an Energy Frontier Research Center funded by the U.S. Department of Energy, Office of Science, under Award Number DE-SC0001294; this award supported the Brookhaven efforts of F.W., S-W. K. and J.G. The XAS measurements by F.W. and L.W. were supported by DOE-EERE under the Batteries for Advanced Transportation Technologies (BATT) Program (being incorporated into the new Advanced Battery Materials Research (BMR) program), under Contract No. DE-AC02-98CH10886 (being recently changed to new DE-SC0012704). DFT calculations by D-H.S. and K.K., were supported by the World Premier Materials grant funded by the Korea government Ministry of Trade, Industry and Energy. Electrochemical tests in Fig. 2 and electrode fabrication for XAS measurements by J.W., J.V. and J.G. were supported as part of the 'Center on Nanostructuring for Efficient Energy Conversion' (CNEEC), an Energy Frontier Research Center funded by the US Department of Energy, Office of Science, under Award Number DE-SC0001060. S.-W.K. thanks the partial support, whilst completing the writing of the manuscript, from the Nuclear Research and Development Program of National Research Foundation (NRF) funded by the Ministry

of Science, ICT and Future Planning (MSIP), Republic of Korea. Research carried out at the Center for Functional Nanomaterials and National Synchrotron Light Source, Brookhaven National Laboratory, was supported by the US Department of Energy, Office of Basic Energy Sciences, under Contract No. DE-AC02-98CH10886 (being recently changed to new DE-SC0012704).

Author contributions

F.W. and S.-W.K. conceived and designed the experiments. F.W., S.-W.K., L.W., D.S., J.V., J.W. and J.G. conducted the experiments. D.-H.S. and K.K. performed DFT calculation. F.W. and S.-W.K. made the data analysis and wrote the paper. J.G. assisted with data analysis and writing the paper. All authors were involved in revising the paper.

Additional information

Supplementary Information accompanies this paper at <http://www.nature.com/naturecommunications>

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at <http://npg.nature.com/reprintsandpermissions/>

How to cite this article: Wang, F. *et al.* Ternary metal fluorides as high-energy cathodes with low cycling hysteresis. *Nat. Commun.* 6:6668 doi: 10.1038/ncomms7668 (2015).



This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>