



Test Report

Report No : TST20250203678E

Date: Mar.06, 2025

Page 1 of 3

Applicant : Tianjin Hongruida Engineering Plastics Co., Ltd.
Address : 7th Street Industrial Zone, Yixingbu, Beichen District, Tianjin, China
Manufacturer : Tianjin Hongruida Engineering Plastics Co., Ltd.
Address : 7th Street Industrial Zone, Yixingbu, Beichen District, Tianjin, China

The following sample(s) was /were submitted and identified on behalf of the clients as :

Sample Name : PET Polyester Granules
Trademark : 宏瑞达
Sample Model : PET—2025
Sample Description : Graininess
Sample Received Date : Feb.28, 2025
Testing Period : Feb.28, 2025 To Mar.06, 2025
Test Requested : As specified by client, for compliance with Food and Drug Administration.
Test Method : Please refer to next page(s).
Test Result : Please refer to next page(s).

Signed for and on behalf of



Scan QR code
verification of authenticity

Security Code : 8W1LGXH6T

Andy Zheng
Technical Director

This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement. TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel: +86-0769-85088050 E-mail: :tst@tst-test.com Http: www.tst-test.com





Test Report

Report No : TST20250203678E

Date: Mar.06, 2025

Page 2 of 3

Sample Description:

No.	Material
1	PET

Test Result(No.1):

Test Method: As specified in FDA 21 CFR 177.1630

Simulant Used	Test Condition	Result(mg/inch ²)	Limit(mg/inch ²)
Distilled water	250°F 2h	<0.1	0.5
50% ethanol	120°F 24h	<0.1	0.5
95% ethanol	120°F 24h	<0.1	0.5

Note: %= percent by weight



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement. TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel: +86-0769-85088050 E-mail: :tst@tst-test.com Http: www.tst-test.com




Test Report

Report No : TST20250203678E

Date: Mar.06, 2025

Page 3 of 3

Sample pictures:



*** End of Report ***



This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Dongguan True Safety Testing Co., Ltd., this test report shall not be copied except in full and published as advertisement. TST is not responsible for the authenticity of the information provided by the customer, including sample information.

Dongguan True Safety Testing Co., Ltd.
Room 201, No.20, East of Houjie Avenue, Houjie, Dongguan, Guangdong, China
Tel: +86-0769-85088050 E-mail: :tst@tst-test.com Http: www.tst-test.com